

Supplementary information

Polymeric biocompatible iron oxide nanoparticles labeled with peptides for imaging in ovarian cancer

Deepshikha Shahdeo^a, Akanksha Roberts^a, Veerbhan Kesarwani^a, Milena Horvat^b, Raghuraj Singh Chouhan^{b, #}, Sonu Gandhi^{a,c, #}

^a*DBT- National Institute of Animal Biotechnology (DBT-NIAB), Hyderabad-500032, Telangana, India.*

^b*Department of Environmental Sciences, Jožef Stefan Institute, Jamova 39, 1000 Ljubljana, Slovenia.*

^c*Amity Institute of Biotechnology, Amity University, Noida-201301, Uttar Pradesh, India.*

#Corresponding author:

E-mail: raghuraj.singh@ijs.si, Tel: +383 1 588 5268

E-mail: gandhi@niab.org.in, sonugandhi@gmail.com, Tel: +91 40 23120127




Fig. S1. Result from 50 nano second (ns) molecular dynamics simulation. **(a)** RMSD fluctuation, **(b)** Residual RMSF, **(c)** Radius of gyration (Rg).

Table S1. (a.i.) Hydrodynamic diameter and (a.ii.) zeta potential of different nanoconjugates of IONPs.

a.i	Sample	pH 3	pH 7.4	pH 9
IONPs		78	34	168
IONPs/C		77	51	945
IONPs/C-G		659	65	3478
IONPs/C-S		940	66	1527
IONPs/C-GS		637	77	3980
a.ii				
	Sample	pH 3	pH 7.4	pH 9
IONPs		16.3	-24	-21
IONPs/C		7.2	22	2.7
IONPs/C-G		21.4	21	-7.86
IONPs/C-S		9.9	20	-8.4
IONPs/C-GS		24.9	18	-15.35